Document Code	:	TDS.02200
Date	:	24.04.2011
Revision Nr.	:	2.1.0
Page	:	1/1

Color Way HPW™ Series

WATER BASED

Color Way HPW[™] Series is the water based solution for the market requirements for PVC&Phthalate-Free inks. Color Way HPW[™] inks are ecological water based inks with economical prices. Recommended substrates for HPW inks are 100% cotton, cotton blends. (*There is also an ink in this series to print on 100% Polyesters). **Note: It is advised to wait for 24 hours before washing.*

* Non-Contamination: HPW Series[™] inks should not be modified or come in contact with any PVC or Phthalate containing ink. Use only recommended additives in order to prevent any contamination. All equipment which comes in contact with HPW Series inks (like mixing apparatus, squeegees, buckets, flood bars, screens, etc.) must be cleaned properly (free of inks or materials which may contaminate the HPW Series inks) before every use.



Technical Data Sheet

FEATURES

- PVC & Phthalate Free!
- Ready to print
- Economical

PRINTER'S GUIDE	
Bleed Resistance	Excellent
Stencil Type	Most direct emulsion stencils are suitable.
Mesh	43-77 t/cm (110-195 t/in)
Retarder	PWB-R10 Retarding Agent / Up to 3% by weight may be added to soften the hand and retard curing time. This also reduces the viscosity of the ink.
Fixing Agent	PWB-F44 Fixing Agent / Up to 2% by weight (<i>recommended</i>) or HPW-940 Fixing Agent / Up to 1% by weight may be added to increase fixing on difficult substrates and improving washing fastness. Adding more than specified will harden the feel and block the screen.
Thickener	PWB-T20 Thickener / Up to 3% by weight (<i>recommended</i>) or HPW-930 Thickener / Up to 5% by weight
Curing Information	150-170°C (302-338°F) / 1-3 minutes However, factors such as ink film thickness, curing equipment and fabric may influence the optimum cure time.
Storage	5-25°C (41-77°F). Avoid direct sun.
Cleanup	Water

Pastes		HPW-415	Foil-Resist Base	HPW-910	Emulsifier	
HPW-105	Rotation Mat-White	HPW-510	Crackle White	HPW-920	Softener	
HPW-111	Ultra Mat-White	HPW-515	Crackle Base	HPW-930	Thickener	
HPW-210	Dark Floor Base	HPW-610	Metallic Base	HPW-940	Fixing Agent	
HPW-220	Discharge White	HPW-620	Glitter Base	HPW-960	Anti-Foam Agent	
HPW-225	Discharge Base	HPW-630	Pearlescent Base	HPW-970	Binder	
HPW-228	Discharge Activator ST	HPW-640	Puff Base	HPW-F20	Flock Adhesive Cross B	
HPW-229	Discharge Activator EC	HPW-710	Glitter Base (for spraying)	Special Ef	Special Effects	
HPW-310	Printing Paste (w. gas)	HPW-720	Ultra Mat-White (for spraying)	HPW-F15	Flock Adhesive	
HPW-320	Polyester Paste	HPW-730	Thinner (for spraying)	HPW-V15	Foil Adhesive	
HPW-410	Foil-Resist White	Additives				

* All recommendation and statements made, if any, are based on Renk Yolu Kimya's research and experience. However, since Renk Yolu Kimya has no control over the conditions of use or storage of the product sold, Renk Yolu Kimya cannot guarantee the results obtained through the use of its products. All products are sold and samples given without any representation or warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where protective rights of third parties involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

Renk Yolu Kimya San. Tic. Ltd. Şti.

Headquarters Cumhuriyet Cad. Baglar Sok. No:2/1 34212 Gunesli - Istanbul / Turkey

Factory Buyuk Kilicli Yolu Cad. No:16 34570 Silivri - Istanbul / Turkey